

STEEL PLATES FROM HOT ROLLED COILS

Qualità: S420MC

Micro Alloyed Steel

Grade **S420MC**

Norm **EN10149-2**

W. Nr. **1.0980**

Rolling state **AR- As rolled**

Description High strength steel for cold-forming, thermomechanically-rolled. This steel grade offers excellent bending, flanging, cold-bordering and folding properties in both longitudinal and transverse direction

Applications Cold formed parts for all type of vehicles, industrial tanks, containers and agricultural equipment

Standard coils' stock range

Dimensions other than the ones listed here can be sourced on agreement.

At times, some of the dimensions listed here might be unavailable: please make sure to get in touch with our sales department for a real-time update about the actual stock availability.

	1500	2000
2	• •	
3	• •	
4	• •	
5	• •	
6	• •	
7	•	
8	•	•
10	•	•
12	• •	•

• = S420MC pickled and oiled

Chemical composition According to UNI EN 10025

Element	Al	B	C	Ceq	Cr	Cu	Mo	Mn	N
Min.	0,015								
Max			0,12					1,60	

Element	Ni	Nb	P	S	Si	Sn	Ti	V	Zr
Min.									
Max		0,09	0,025	0,015	0,50		0,15	0,2	

Mechanical properties According to UNI EN 10025

Nominal Thickness (mm)	-
Yield Strenght (MPa)	≥ 420
Nominal Thickness (mm)	-
Tensile Strenght (MPa)	480 – 620

Nominal Thickness (mm)	< 3	≥ 3
Elongation A80%	≥ 16	
Elongation A5%	≥ 19	
Temperature (°C)	-20°C (where reported in the MTC)	
Notch Impact Energy (J)	≥ 40	

Tolerances

Dimensional Tolerances

UNI EN 10051

Surface Status

UNI EN 10163-2

Equivalences

W. Nr.	Germany SEW	France AFNOR	England BS
1.0980	QStE420TM	E420D	HR50F45

Certifications

- EN10204-3.1

DISCLAIMER: while great care has been taken to ensure the accuracy of all information contained in this document, Siderurgica Astico S.p.A. hereby disclaims any and all responsibility or liability that may be asserted or claimed arising from, or claimed to have arisen from, reliance upon the use or the interpretation of this document by any person. This document may be subject to change at any time without warning.